

TNPL PLATINUM

PLAIN COPIER PAPER

VALUE PACK

- High brightness and opacity
- Dimensional stability and stiffness
- Improved electrostatic properties
- Offers you absolute copying freedom

A4

21 x 29.7 cm
500 sheets
Net Wt: 2.34 kg



**New
Improved**

Absolute Copying Freedom

Get the best out of your copier paper

- Do not keep paper in cold or damp environment
- Allow the ream to reach the room temperature before using it
- Always open each ream as you use it
- Avoid leaving paper unprotected in machines for long periods
- Fan the paper block well before loading



IS 14001



CM/L - 6100045986

For BIS certification details
please visit www.bis.gov.in




Plg. Mfr. Mtd. By : JR IMPRESSIONS
EPR Reg No. : 2025070108544872271
BOPP Used : 15 Microns



TNPL PLATINUM
PLAIN COPIER PAPER
Absolute Copying Freedom

75 GSM



TNPL

PLATINUM

PLAIN COPIER PAPER

Brand :  **TNPL**
Variety : Plain Copier Paper
GSM : 80 g/m²
Thickness : 105 micron +/- 5%
Sheet Size : A4 Width: 21 cm;
Length: 29.7 cm
Sheet Qty. : 500 Nos
Net Weight : 2.49 kg
Packed on : 09-10-2022 05:45
MRP / Lot No. :  389- RME2385412
(Incl. of all taxes)

Manufactured & Packed by:
Tamil Nadu Newsprint and Papers Limited
No. 141, TNPL Road, Kagithapuram,
Pugalur-Taluk, Karur District - 639 138,
Tamil Nadu, India. Ph: +91-4324-277001-9

Registered office:
Tamil Nadu Newsprint and Papers Limited
No. 67, Mount Road, Guindy,
Chennai - 600 032, India.
Phone : +91-44-2235 4415-16,
Fax: +91-44-2235 3834, Web: www.tnpl.com

In case of any Consumer complaints,
please contact

Senior Manager - Customer Care
(No. 67, Mount Road, Guindy,
Chennai 600 032)

A4 **80**
GSM



TAMILNADU NEWSPRINT AND PAPERS LIMITED
67, Mount Road, Guindy, Chennai, Pin:600032
Ph:044-22354415 Email:mktg.co@tnpl.co.in

TNPL COPIER PLATINUM - Specifications

S.No	Property	Specification
1	Nominal GSM (g/m ²)	70 / 75 / 80
2	Substance Tolerance	± 2.5 %
3	Caliper (Micron)	100 / 102 / 105
4	Moisture %	6.0 ± 0.5
5	Bendsten Smoothness TS ml/min	150 - 250
6	Bendsten Smoothness WS ml/min	150 - 220
7	Porosity ml/min (Max)	650
8	Cobb 60 g/m ² (Max)	30
9	Brightness ISO % (Min)	89
10	Opacity %	92 - 93
11	CIE Whiteness	155 ± 5